

Specifications:	
-----------------	--

- Concrete Minimum Compressive Strength 4,000 psi @ 28 days
- Concrete Air Entrainment : 4% 9%
- Type I, or Type I/II Cement
- Steel Reinforcement :

#4 Deformed Bar (Gr.60) ASTM A-615, or equal

- Meets HS-20 Wheel Load
- Fiber Mesh Reinforcement ASTM C-1116 @ a Rate of 4.0 lbs/cy
- · Cast-in Utility Anchors Where Needed, for Handling

Product #	I.D.	O.D.	HGT.	W.T.
SGR-03-2436	24"	36"	3"	6"
SGR-04-2436	24"	36"	4"	6"
SGR-06-2436	24"	36"	6"	6"
SGR-12-2436	24"	36"	12"	6"
SGR-03-2440	24"	40"	3"	8"
SGR-04-2440	24"	40"	4"	8"
SGR-06-2440	24"	40"	6"	8"
SGR-04-3040	30"	40"	4"	5"
SGR-06-3040	30"	40"	6"	5"

NOTES: STACKABLE GRADE RING		EASTERN PRECAST  COMPANY, INCORPORATED  2 COMMERCE DRIVE, BROOKFIELD, CT 06804 PHONE: (203) 775 - 0230 FAX: (203) 740 - 2059 WWW.EASTERNPRECAST.COM				
			CONCRETE GRADE RING			
MATERIAL:			MODEL NO.	SGR		
	DWNG DATE: 11/13/2017	TOLERANCE	LOAD RATING	H - 20		
BY: DATE:	DATE :			REVISION 1 - DATE		REV
	CHKD DATE :		REVISION 2 - DATE			